

SMAW Electrodes

- High Tensile & High Yield Strength Steel

GL98M

AWS A5.5M E6218M / A5.5 E9018M
JIS Z 3211 E6218-N3M1
ISO 18275-A-E 55 5 Z B

Product Features:

- Iron powder low hydrogen coated electrode for low alloy high yield and high tensile strength steel.
- Good arc stability, less spatter loss and suitable for all positions.
- Good for RT examination, good mechanical properties.
- Low moisture absorption flux to get good crack resistance.

Applications:

- Suitable for welding of 620 N/mm² grade low alloy steel or similar grade steels on pressure vessels and general steel structures.

Typical chemical composition of all-weld metal (wt%)

C	Si	Mn	Cr	Ni	Fe
0.07	0.66	1.20	0.03	1.47	Bal.

Typical mechanical properties of all weld metal

Yield Strength N/mm ²	Tensile Strength N/mm ²	Elongation %	Impact value (-50°C) J
579	641	28	77

Size (mm) & recommended welding parameters (A) DC+

Diameter / Length	3.2/350	4.0/400	5.0/450
Flat position	90~140	150~200	220~270
Vertical / overhead position	80~110	120~150	-

Note:

- 300~350°C x 1hr baking prior to use.

Goodweld Corporation
No.99, Huangong Rd. Yongkang Tainan, Taiwan
Phone: 886-6-2331003 Fax: 886-6-2333213
All Right Reserved


GOODWELD
www.goodweld.com.tw