

SMAW Electrodes

ND150L

AWS A5.1M E4319 / A5.1 E6019
JIS Z 3211 E4319U
ISO 2560-A-E 35 2 RA

Product Features:

- Ilmenite type covered electrode for mild steel is available to process full positions welding.
- Available for high current welding.
- Good slag removal.
- Good for RT examination, good mechanical properties.

Applications:

- Suitable for welding of thickness ≤ 20 mm steel structures on shipbuilding, vehicles, buildings, bridges, tanks, pressure vessels and general mechanical structures.

Typical chemical composition of all weld metal (wt%)

C	Si	Mn	P	S	Fe
0.10	0.06	0.43	0.024	0.006	Bal.

Typical mechanical properties of all weld metal

Yield Strength N/mm ²	Tensile Strength N/mm ²	Elongation %	Impact value (-20°C) J
406	471	29	65

Size (mm) & recommended welding parameters (A) AC or DC±

Diameter / Length	2.6/300	3.2/350	4.0/400	5.0/450	6.0/450
Flat position	60~80	100~140	140~190	190~240	240~320
Vertical / overhead position	50~70	80~110	120~160	150~200	-

Note:

Goodweld Corporation
No.99, Huangong Rd. Yongkang Tainan, Taiwan
Phone: 886-6-2331003 Fax: 886-6-2333213
All Right Reserved

GOOD
GOODWELD
www.goodweld.com.tw