

SMAW Electrodes for Chromium-Molybdenum Low Alloy Steels

GL86B6 / GL88B6

AWS A5.5M E5516(8)-B6
A5.5 E8016(8)-B6
JIS Z 3223 E5516(8)-5CM

Product Features:

- Low hydrogen/ iron powder type covered electrode for low alloy heat resistant steel.
- Very low hydrogen contained in weld metal.
- All deposited weld metal contains approximately 5.0%Cr- 0.5%Mo alloy elements, good for serving temperature $\leq 550^{\circ}\text{C}$.
- Good for RT examination, good mechanical properties.

Applications:

- Suitable for welding of ASTM A387 Gr5 and A335 Gr.P5 steel and similar grade steels.

Typical chemical composition of all-weld metal (wt%)

C	Si	Mn	Cr	Mo
0.07	0.58	0.79	4.73	0.58

Typical mechanical properties of all weld metal

Yield Strength N/mm ²	Tensile Strength N/mm ²	Elongation %	Post Weld Heat Treatment (PWHT) °C×1hr
664	722	22	740

Size (mm) & recommended welding parameters (A) AC or DC+

Diameter / Length	2.6/300	3.2/350	4.0/400	5.0/450
Flat position	60~90	90~140	150~200	220~270
Vertical / overhead position	50~80	80~110	120~150	--

Note:

- 300~350°C x 1hr baking prior to use.

Goodweld Corporation
No.99, Huangong Rd. Yongkang Tainan, Taiwan
Phone: 886-6-2331003 Fax: 886-6-2333213
All Right Reserved

GOOD
GOODWELD
www.goodweld.com.tw