

S.S. - Submerged Arc Welding Wire

GS308 / GS308L

AWS A5.9 ER308(L)
JIS Z 3324 YS308(L)

Applications:

- Suitable for welding of SUS304, 302, 305.

Typical chemical composition of wire (wt%)

Wire diameter (mm)	C	Si	Mn	Ni	Cr
308	0.05	0.48	1.95	9.7	19.9
308L	0.03	0.47	1.41	10.2	19.8

Note: