

# Metal to metal abrasion resistant

## **GH350R**

JIS Z 3251 DF2A-350R

### Product Features:

- Weld metal typical hardness approximately HRC35.
- High welding performance, low spatter loss and good bead appearance.
- Good cutting workability.

### Applications:

- Suitable for hardfacing repair welding of machinery; carbon steel, cast iron and hardenable alloy steel repair and fabrication welding.

Typical chemical composition of all-weld metal (wt%)

C	Si	Mn	Cr	Mo
0.11	0.37	0.86	2.37	0.63

Typical hardness of weld metal

As welded HRC	layers
36	3

Size (mm) & recommended welding parameters (A)

Diameter / Length	2.6/300	3.2/350	4.0/400	5.0/350/450	6.0/450
Flat position	70~100	100~140	140~190	180~230	240~300

### Note:

- 100~120°C x 1 hr baking prior to use.
- Keep short arc length while welding.
- 150°C preheating temperature on base metal before welding.

Goodweld Corporation  
No.99, Huangong Rd. Yongkang Tainan, Taiwan  
Phone: 886-6-2331003 Fax: 886-6-2333213  
All Right Reserved

**GOOD**  
**GOODWELD**  
[www.goodweld.com.tw](http://www.goodweld.com.tw)