Metal to sand abrasion resistant

MXW R117

Product Features:

- Self or gas shield type hardfacing flux cored arc welding wire.
- Good for impact and abrasion resistance.
- Small stress relieve crack on weld metal surface.

Applications:

 Suitable for repair welding of worn out machine parts such as coned crusher receivers, mantles, hammer crusher, cane knifes and crusher rollers, etc.

Typical chemical composition of all-weld metal (wt%)					
С	Si	Mn	Cr	Мо	
2.53	1.46	1.57	10.86	1.79	

Typical characteristics of weld metal				
Abrasion Resistance	Impact Resistance	Welding layer	Hardness HRC	
Excellent	Excellent	3	52	

Size & recommended welding parameters					
Diameter	1.2mm	1.6mm			
Polarity	DC+	DC+			
Ampere	150~320	180~340			
Voltage	25~33	26~35			
Wire extension	15~30mm	15~30mm			
Shielding Gas	Self Shield (no gas shield) / CO2	Self Shield (no gas shield) / CO ₂			

Note:

All values listed on the table obtained from non-gas shielded welding test.

