

# Nickel Base Alloy SMAW Electrodes

## GNI 132

AWS A5.11 ENiCrFe-1  
ISO 14172-E Ni 6062  
JIS Z 3224 E Ni 6062

### Product Features:

- Low hydrogen type nickel base covered electrode for DC+ only.
- High welding performance.
- Good bead appearance and crack resistance.
- Good heat and corrosion resistance.
- Good low temperature impact toughness.
- Easy Slag removal.

### Applications:

- Welding of similar grade of nickel base alloy.
- Welding of 9% Ni steel.
- Welding overlay to carbon, stainless and Ni steels.

Typical chemical composition of all-weld metal (wt%)

C	Si	Mn	Ni	Cr	Nb	Fe
0.028	0.53	2.29	69.4	16.6	2.09	8.95

Typical mechanical properties of all-weld metal

Yield Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation	Impact (-196°C) J
387	615	39	73

Size (mm) & recommended welding parameters (A)

Diameter	2.6/300	3.2/350	4.0/350
Flat position	65~85	70~110	95~150

### Note:

1. 300 ~ 350°C x 1hr baking prior to use.
2. Recommend short arc length and low current, electrode positive (DC+).
3. Full cleaning before welding.

Goodweld Corporation  
No.99, Huangong Rd. Yongkang Tainan, Taiwan  
Phone: 886-6-2331003 Fax: 886-6-2333213  
All Right Reserved

**GOOD**  
**GOODWELD**  
www.goodweld.com.tw