

Cast Iron SMAW Electrodes

GC0

AWS A5.15 ESt
ISO 1071-ECSt 1
JIS Z 3252 ECSt N

Product Features:

- Low hydrogen type covered electrode for cast iron welding and repair.
- Using GC100 or GC55 for first layer and GC0 for the others to save cost.

Applications:

- Suitable for cast iron welding and repair welding under high temperature and non-post machining required condition.

Typical chemical composition of all-weld metal (wt%)

C	Si	Mn	P	S
1.1	0.75	0.56	0.023	0.008

Note: No specific all weld metal chemical composition on Est, above analysis data is for reference.

Typical mechanical properties of all-weld metal

Hardness HV
250

Size (mm) & recommended welding parameters (A) AC or DC+

Diameter / Length	2.6/300	3.2/350	4.0/400	5.0/450
Flat position	60~90	85~120	120~150	150~220

Note:

Goodweld Corporation
No.99, Huangong Rd. Yongkang Tainan, Taiwan
Phone: 886-6-2331003 Fax: 886-6-2333213
All Right Reserved

GOOD
GOODWELD
www.goodweld.com.tw